# **Submittal Information**

# Large Diameter Tapcon (LDT) Self-threading

#### **SPECIFIED FOR ANCHORAGE INTO CONCRETE**

The LDT anchor is a high performance anchor that cuts its own threads into concrete.

Anchor bodies are made of hardened carbon steel and zinc plated. **Grade 5** 

The anchors shall have a finished hex washer head with anti-rotation serrations to prevent anchor back-out. The head of the anchor is stamped with a length identification code for easy inspection.

The anchor shall be installed with carbide tipped hammer drill bits made in accordance to ANSI B212.15-1994.

#### LDT 3/8" and 1/2" are available with EnvireX coating

1,000 hours salt spray ASTM B117. Approved for use in ACQ and MCQ lumber\*

\*Excessive content of copper in the ACQ and MCQ lumber may affect the anchor finish.

### **INSTALLATION STEPS**

Installation Steps for Concrete, Lightweight Concrete and Metal Deck



 Using the proper size carbide bit (see chart) drill a pilot hole at least 1" deeper than anchor embedment.



 Using an electric impact wrench, or socket wrench (hand install) insert anchor into hole and tighten anchor until fully seated. (see chart for socket size) (do not over tighten).

#### Installation Steps for Hollow or Grout-Filled CMU

(3/8" and 1/2" diameter)



 Using a 5/16" (for 3/8" LDT) or 7/16" (for 1/2" LDT) carbide tipped bit, drill a pilot hole at least 1" deeper than anchor embedment.



**2.** Using a socket wrench insert anchor into hole and hand tighten (only) anchor until fully seated. (9/16" socket for 3/8" and 3/4" socket for 1/2") (do not over tighten).

#### **LENGTH INDICATION CODE\***

CODE	LENGTH OF ANCHOR In. (mm)								
Α	1-1/2 < 2	(38.1 < 50.8)							
В	2 < 2-1/2	(50.8 < 63.5)							
С	2-1/2 < 3	(63.5 < 76.2)							
D	3 < 3-1/2	(76.2 < 88.9)							
E	3-1/4 < 4	(88.9 < 101.6)							
F	4 < 4-1/2	(101.6 < 114.3)							
G	4-1/2 < 5	(114.3 < 127.0)							
Н	5 < 5-1/2	(127.0 < 139.7)							

<sup>\*</sup> Located on top of anchor for easy inspection.

# LDT's can be installed by hand or with an impact wrench

Installation by hand—is easy, simply using a socket wrench



Installation by impact wrench—is recommended for faster installations or for high volume projects. Installation with impact wrench—is **not** recommended for hollow block.

#### **Selection Chart**

LDT Size	ANSI Standard	Anchor Head	Washer Diameter	B Minimum	© Hole	USE IN		
	Drill Bit	(Socket Size)		Embedment	Depth		CN	ΛU
	Diameter	Diameter				Concrete	Hollow	<b>Grout-filled</b>
LDT 3/8"	5/16"	9/16"	13/16"	1-1/2"	2-1/2"	YES	YES	YES
LDT 1/2"	7/16"	3/4"	1″	2-1/2"	3-1/2"	YES	NO	YES
LDT 5/8"	1/2"	13/16"	1-3/16"	2-3/4"	3-3/4"	YES	NO	YES
LDT 3/4"	5/8"	15/16"	1-5/16"	3-1/4"	4-1/4"	YES	NO	YES

<sup>©</sup> See catalog for effective lengths and length indication code.



## **Submittal Information**

#### PERFORMANCE TABLES

### LDT Anchors Ultimate Tension and Shear Values (Lbs/kN) in Concrete

ANCHOR	EMBI	EDMENT	f'c = 2000 PSI (13.8 MPa)				f'c = 3000 PSI (20.7 MPa)				f'c = 4000 PSI (27.6 MPa)			
DIA. In. (mm)	DEPTH In. (mm)			TENSION Lbs. (kN)		SHEAR Lbs. (kN)		TENSION Lbs. (kN)		SHEAR Lbs. (kN)		SION (kn)	SHEAR Lbs. (kN)	
3/8 (9.5)	1-1/2	(38.1)	1,336	(5.9)	2,108	(9.4)	1,652	(7.3)	2,764	(12.3)	1,968	(8.8)	3,416	(15.2)
	2	(50.8)	1,492	(6.6)	3,036	(13.5)	2,024	(9.0)	3,228	(14.4)	2,552	(11.4)	3,420	(15.2)
	2-1/2	(63.5)	3,732	(16.6)	3,312	(14.7)	3,748	(16.7)	3,364	(15.0)	3,760	(16.7)	3,424	(15.2)
	3-1/2	(88.9)	5,396	(24.0)	3,312	(14.7)	6,624	(29.5)	3,368	(15.0)	7,852	(34.9)	3,428	(15.2)
1/2 (12.7)	2	(50.8)	3,580	(15.9)	5,644	(25.1)	3,908	(17.4)	6,512	(29.0)	4,236	(18.8)	7,380	(32.8)
	3-1/2	(88.9)	7,252	(32.3)	6,436	(28.6)	8,044	(35.8)	7,288	(32.4)	8,836	(39.3)	8,140	(36.2)
	4-1/2	(114.3)	10,176	(45.3)	7,384	(32.8)	10,332	(46.0)	7,968	(35.4)	10,488	(46.7)	8,552	(38.0)
5/8 (15.9)	2-3/4	(69.9)	5,276	(23.5)	8,656	(38.5)	6,560	(29.2)	11,064	(49.2)	7,844	(34.8)	13,476	(59.9)
	3-1/2	(88.9)	7,972	(35.5)	10,224	(45.5)	9,848	(43.8)	12,144	(54.0)	11,724	(52.2)	14,060	(62.5)
	4-1/2	(114.3)	11,568	(51.5)	12,316	(54.8)	13,432	(59.8)	13,580	(60.4)	16,892	(75.1)	14,840	(66.0)
3/4 (19.1)	3-1/4	(82.6)	6,876	(30.6)	7,140	(31.8)	9,756	(43.4)	10,728	(47.7)	12,636	(56.2)	14,316	(63.6)
	4-1/2	(114.3)	10,304	(45.8)	13,120	(58.4)	14,424	(64.2)	16,868	(75.0)	18,540	(82.5)	20,612	(91.7)
	5-1/2	(139.7)	13,048	(58.0)	17,908	(79.7)	18,156	(80.8)	21,718	(96.9)	23,268	(130.5)	25,652	(114.1)

# Allowable Tension and Shear Values\* (Lbs/kN) in Concrete Carbon and Stainless Steel

	car oon and otamicos oteer														
ANCHOR	EMB	EDMENT	f'c = 2000 PSI (13.8 MPa)				f'c = 3000 PSI (20.7 MPa)				f'c = 4000 P	SI (27.6 MPa)			
DIA. In. (mm)	DEPTH In. (mm)		TENSION Lbs. (kN)		SHEAR Lbs. (kN)			TENSION Lbs. (kN)		SHEAR Lbs. (kN)		TENSION Lbs. (kN)		SHEAR Lbs. (kN)	
3/8 (9.5)	1-1/2	(38.1)	334	(1.5)	527	(2.3)	413	(1.8)	691	(3.1)	492	(2.1)	854	(3.8)	
	2	(50.8)	373	(1.7)	759	(3.4)	506	(2.2)	807	(3.6)	638	(2.8)	855	(3.8)	
	2-1/2	(63.5)	933	(4.2)	828	(3.7)	937	(4.2)	841	(3.7)	940	(4.2)	856	(3.8)	
	3-1/2	(88.9)	1,349	(6.0)	828	(3.7)	1,656	(7.4)	842	(3.7)	1,963	(8.7)	857	(3.8)	
1/2 (12.7)	2	(50.8)	895	(4.0)	1,411	(6.3)	977	(4.3)	1,628	(7.2)	1,059	(4.7)	1,845	(8.2)	
	3-1/2	(88.9)	1,813	(8.0)	1,609	(7.2)	2,011	(8.9)	1,822	(8.1)	2,209	(9.8)	2,035	(9.0)	
	4-1/2	(114.3)	2,544	(11.3)	1,846	(8.2)	2,583	(11.5)	1,992	(8.9)	2,622	(11.7)	2,138	(9.5)	
5/8 (15.9)	2-3/4	(69.9)	1,319	(5.9)	2,164	(9.7)	1,640	(7.3)	2,766	(12.3)	1,961	(8.7)	3,369	(15.0)	
	3-1/2	(88.9)	1,993	(8.9)	2,556	(11.4)	2,462	(10.9)	3,036	(13.5)	2,931	(13.0)	3,515	(15.6)	
	4-1/2	(114.3)	2,892	(12.9)	3,079	(13.7)	3,358	(14.9)	3,395	(15.1)	4,223	(18.8)	3,710	(16.5)	
3/4 (19.1)	3-1/4	(82.6)	1,719	(7.6)	1,785	(7.9)	2,439	(10.8)	2,682	(11.9)	3,159	(14.0)	3,579	(15.9)	
	4-1/2	(114.3)	2,576	(11.5)	3,280	(14.6)	3,606	(16.0)	4,217	(18.7)	4,635	(20.6)	5,153	(22.9)	
	5-1/2	(139.7)	3,262	(14.5)	4,477	(19.9)	4,539	(20.2)	5,445	(24.2)	5,817	(25.9)	6,413	(28.5)	

<sup>\*</sup> Allowable values are based upon a 4 to 1 safety factor. (Ultimate/4)

# Recommended Edge & Spacing Requirements for Tension Loads\* LDT Anchors Carbon and Stainless Steel

		`									
ANCHOR DIA. In. (mm)		EMBEDMENT DEPTH In. (mm)		EDGE DISTANCE REQUIRED TO OBTAIN MAX. WORKING LOAD In. (mm)		LOAD FACTOR APPLIED AT MIN. EDGE DISTANCE 1-3/4 Inches (44mm)	REQUIREI Max. Wo	DISTANCE D TO OBTAIN RKING LOAD (mm)	LOAD FACTOR APPLIED AT MIN. SPACING DISTANCE 3 Inches (76mm)		
3/8	(9.5)	1-1/2	(38.1)	2	(50.8)	70%	6	(152.4)	44%		
		2	(50.8)	2	(50.8)	70%	6	(152.4)	44%		
		2-1/2	(63.5)	3	(76.2)	70%	6	(152.4)	44%		
		3-1/2	(88.9)	4	(101.6)	70%	6	(152.4)	44%		
1/2	(12.7)	2	(50.8)	2-1/4	(57.2)	65%	8	(203.2)	27%		
		3-1/2	(88.9)	3	(76.2)	65%	8	(203.2)	27%		
		4-1/2	(114.3)	4	(101.6)	65%	8	(203.2)	27%		

<sup>\*</sup> Edge and spacing distance shall be divided by .75 when anchors are placed in structural lightweight concrete. Linear interpolation may be used for intermediate spacing and edge distances.

For 5/8" and 3/4" LDT Anchors, the critical edge distance for these anchors is 10 times the anchor diameter. The edge distance of these anchors may be reduced to 1-3/4" provided a 0.65 load factor is used for tension loads, a 0.15 load factor is used for shear loads applied perpendicular to the edge, or a 0.60 load factor is used for shear loads applied perpendicular to the edge distances.



# **Submittal Information**

#### PERFORMANCE TABLES

#### Recommended Edge & Spacing Requirements for Shear Loads\* LDT Anchors Carbon and Stainless Steel

	HOR DIA. . (mm)	EMBEDMENT DEPTH In. (mm)		EDGE DISTANCE REQUIRED TO OBTAIN MAX. WORKING LOAD In. (mm)		LOAD FACTOR APPLIED AT MIN. EDGE DISTANCE 1-3/4 Inches (44mm)	REQUIRE MAX. WO	G DISTANCE D TO OBTAIN PRKING LOAD . (mm)	LOAD FACTOR APPLIED AT MIN. SPACING DISTANCE 3 Inches (76mm)	
3/8	(9.5)	1-1/2	(38.1)	3	(76.2)	25%	6	(152.4)	57%	
		2	(50.8)	4	(101.6)	25%	6	(152.4)	57%	
		2-1/2	(63.5)	5	(127.0)	25%	6	(152.4)	57%	
		3-1/2	(88.9)	5	(127.0)	25%	6	(152.4)	57%	
1/2	(12.7)	2	(50.8)	5	(127.0)	25%	8	(203.2)	60%	
		3-1/2	(88.9)	5	(127.0)	25%	8	(203.2)	60%	
		4-1/2	(114.3)	5-1/2	(139.7)	25%	8	(203.2)	60%	

<sup>\*</sup> Edge and spacing distances shall be divided by .75 when anchors are placed in structural lightweight concrete. Linear interpolation may be used for intermediate spacing and edge distances.


### **Ultimate Tension Load (Lbs/kN) in Concrete Block** LDT Anchors (anchors should be installed by hand in hollow block)

ANCHOR DIA. In. (mm)	EMBEDMENT DEPTH	HOLLOW CON	ICRETE BLOCK	GROUT FILLED CONCRETE BLOCK			
()	In. (mm)	TENSION Lbs. (kN)	SHEAR Lbs. (kN)	TENSION Lbs. (kN)	SHEAR Lbs. (kN)		
3/8 (9.5)	1-1/2 (38.1)	916 (4.1)	3,176 (14.1)	1,592 (7.1)	3,900 (17.3)		
1/2 (12.7)	2-1/2 (63.5)	N/A	N/A	5,924 (26.4)	6,680 (29.7)		

### Allowable Tension and Shear\* (Lbs/kN) in Concrete Block LDT Anchors (anchors should be installed by hand in hollow block)

ANCHOR DIA. In. (mm)	EMBEDMENT DEPTH	HOLLOW COM	ICRETE BLOCK	GROUT FILLED CONCRETE BLOCK			
()	In. (mm)	TENSION Lbs. (kN)	SHEAR Lbs. (kN)	TENSION Lbs. (kN)	SHEAR Lbs. (kN)		
3/8 (9.5)	1-1/2 (38.1)	229 (1.0)	794 (3.5)	398 (1.8)	975 (4.3)		
1/2 (12.7)	2-1/2 (63.5)	N/A	N/A	1,481 (6.6)	1,670 (7.4)		

<sup>\*</sup>Allowable values are based upon a 4 to 1 safety factor. (Ultimate/4)



### Anchoring Overhead in 3000 PSI Lightweight LDT Anchors Concrete On Metal Deck

ANCHOR	DRILL HOLE	EMBEDMENT		3000P	SI (20.7 MPa)	) CONCRETE		
In (mm)	DIAMETER	In. (mm)	ULTIMATE TENSION LOAD		ALLOWABLE WORKING LOAD			
In. (mm)		Lbs. (kN)			Lbs. (kN)			
3/8" LDT	5/16 (7.9)	1-1/2 (38.1)	Upper Flute 2,889		(12.9)	722 (3.2)		
			Lower Flute	1,862	(8.3)	465 (2.1)		